

TECHNICAL SPECIFICATIONS

Primero dryback



PRODUCT INFORMATION		
Level of use	EN ISO 10874	23 - 31
Total thickness	EN ISO 24346	2,25 mm (89 mils)
Wear layer	EN ISO 24340	0,3 mm (12 mils)
Wear layer PUR treatment		Superguard®
Total weight g/m²	EN ISO 23997	3.714
SIZE & PACKING		
Planks	EN ISO 24342	16,3 x 98,8 cm (6,42" x 38,90")
Tiles A	EN ISO 24342	32,9 x 65,9 cm (12,95" x 25,94")
Tiles B	EN ISO 24342	49,3 x 49,3 cm (19,41" x 19,41")
Box planks	24 pcs/box	3,87 m²/box (41,6 ft²/box)
Box Tiles A	18 pcs/box	3,90 m²/box (42,01 ft²/box)
Box Tiles B	16 pcs/box	3,89 m²/box (41,86 ft²/box)
TEST RESULTS		
Inflammability	EN 13501	Bfl-S1
Scratch resistance	EN 660-2	Class T
Squareness & straightness	EN ISO 24342	≤ 0,25 mm (Tiles B) ≤ 0,35 mm (Planks & Tiles A)
Slip resistance	EN 13893	DS
Slip restraint	DIN 51130	R10
Residual indentation	EN ISO 24343	≤ 0,10 mm
Furniture leg resistance	EN ISO 16581	No cracks, no damage
Curling	EN ISO 23999	≤ 2 mm
Electrical resistance	EN 1081	≤ 10 ⁹ Ohm
Dimensional stability	EN ISO 23999	Norm: ≤ 0,25 % Average result measured: ≤ 0,05 %
Heat insulation	EN 12524	0,25 w/(m.K)
Thermal resistance R	EN ISO 12664	0,01 m².K/W
Electrostatic performance	EN 1815	< 2 kV
Formaldehyde group	EN 717-1	E1
Acoustic insulation	EN 140-8	4 dB
Castor chair resistance	EN 425	No damage to wearlayer, no delamination
Stain resistance	EN ISO 26987	Very good
Light fastness	ISO 105-B02	≥6
Underfloor heating	EN 12524	Suitable, max 27°C
Warranty (year)		12 Residential 5 Commercial

Primero click

PRODUCT INFORMATION		
Level of use	EN ISO 10874	23 - 31
Total thickness	EN ISO 24346	4,5 mm (180 mils)
Wear layer	EN ISO 24340	0,3 mm (12 mils)
Wear layer PUR treatment		Superguard®
Total weight g/m²	EN ISO 23997	7.821
SIZE & PACKING		
Planks	EN ISO 24342	19,1 x 131,6 cm (7,52" x 51,81")
Tiles	EN ISO 24342	32,4 x 65,5 cm (12,76" x 25,79")
Box planks	7 pcs/box	1,76 m²/box (18,94 ft²/box)
Box Tiles	7 pcs/box	1,49 m²/box (15,99 ft²/box)
TEST RESULTS		
Inflammability	EN 13501	Bfl-S1
Thermal resistance R	EN ISO 12664	0,0154 m².K/W
Formaldehyde group	EN 717-1	E1

Other test results, see above.

The warranty covers manufacturing defects and premature wear in the event of normal use.

The samples in this presentation are only cuttings of the respective products and show only a small part of the overall design and colour. With regard to colour printing of the photographic images, it is only possible to give a provisional representation of the colour.

